

ISOFLEX NBU 15

Spindle bearing grease



Your benefits at a glance

- Tried and tested over many years especially in high-speed applications
- Longer component life due to optimized wear protection and good pressure absorption capacity
- Excellent resistance to water and media as well as above-average anticorrosive additives protect bearings against premature failure, thus helping to minimize repair costs
- Low intrinsic bearing heat due to low lubricant friction enabling longer service life
- Uninterrupted machine operation due to good pumpability and metering in customary centralized lubricating systems

Your requirements - our solution

ISOFLEX NBU 15 is a high-speed grease with a good pressure absorption capacity.

It consists of a combination of ester oil, synthetic hydrocarbon oil and mineral oil and a barium complex soap. It offers good protection against wear and corrosion and is resistant to water, media and oxidation.

Application

ISOFLEX NBU 15 is primarily used for spindle bearings and high-speed plain bearings, e.g. in machine tools and textile machines. Further applications are in threaded spindles, ball screws operating under high loads, running gear bearings, as a long-term grease in cableway bearings and in precision engineering. It may also be used

for the lubrication of tooth flanks in precision gears (e.g. bevel gears in milling machines, electromechanical valve actuators).

Application notes

The lubricant is applied by brush, spatula, grease gun or grease cartridge. Owing to the many elastomer and plastic compositions, we recommend checking the grease's compatibility prior to series application with elastomers or plastics.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	ISOFLEX NBU 15
Cartridge 400 g	+
Cartridge 400 g	+
Can 1 kg	+
Bucket 5 kg	+
Bucket 25 kg	+
Drum 180 kg	+

Characteristics	ISOFLEX NBU 15
Article number	004026
Colour space	beige

ISOFLEX NBU 15

Spindle bearing grease



Characteristics	ISOFLEX NBU 15
Texture	homogeneous , short fibrous
Service temperature, lower limit	-40 °C
Service temperature, upper limit	130 °C
Density, Klüber method: PN 024, 20°C	approx. 0.99 g/cm ³
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	265 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	295 0.1 mm
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , lower limit	4000 mPas
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , upper limit	8000 mPas
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 100°C	approx. 4.5 mm ² /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 51562-1 / ASTM D445 / ASTM D7042, 40°C	approx. 21 mm ² /s
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 168 h	≤ 1 corrosion degree
Dropping point, DIN ISO 2176 / IP 396	≥ 220 °C
Speed factor (n x dm)	approx. 1600000 mm/min
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx. 36 months	

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 90 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.