

Klübersynth BHP 72-102

High-temperature lubricant with extraordinary anticorrosion properties for lifetime lubrication



Your benefits at a glance

- Long availability of components over a wide service temperature range
 - when exposed to corrosive atmosphere
 - when exposed to high vibrations and loads
- High economic efficiency due to innovative hybrid grease formulation

Your requirements - our solution

Klübersynth BHP 72-102 is an innovative, synthetic long-term lubricating grease based on ester oils and perfluorinated polyether oil (PFPE). Its outstanding characteristics are good oil retention at high permanent temperatures and good corrosion protection as well as water resistance - yet another contribution to a longer bearing life and a higher thermal stability compared to conventional lubricants. In tests performed on component test rigs subject to high permanent temperatures up to 200 °C Klübersynth BHP 72-102 offers an extremely long service life.

Application

Klübersynth BHP 72-102 has been designed for the lifetime lubrication of rolling bearings subject to high loads and alternating temperatures ranging from -40 °C to 200 °C. The product is suitable for the lubrication highly loaded rolling bearings in components close

to automobile engines, e.g. bearings viscocouplings, belt tensioners, water pumps, fans, servomotors and similar applications.

Klübersynth BHP 72-102 forms a stable grease collar that serves as a lubricant reservoir resistant to vibration and at the same time helps to protect the bearings against contaminants.

Application notes

Klübersynth BHP 72-102 can be applied by standard metering systems (brush, spatula, grease gun). Ideally, the bearing should be metallically blank. If any anticorrosive fluid has been applied prior to greasing, we recommend checking compatibility with the lubricant.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübersynth BHP 72-102
Cartrigde 500 g	+
Can 600 g	+
Can 1,2 kg	+
Bucket 7 kg	+
Bucket 20 kg	+
Bucket 25 kg	+

Characteristics	Klübersynth BHP 72-102
Article number	094102
Composition, solid lubricant	PTFE

Klübersynth BHP 72-102

High-temperature lubricant with extraordinary anticorrosion properties for lifetime lubrication



Characteristics	Klübersynth BHP 72-102
Composition, thickener	polyurea
Composition, type of oil	ester oil , PFPE
Colour space	white
Service temperature, lower limit	-40 °C
Service temperature, upper limit	200 °C
Density, Klüber method: PN 024, 20°C	approx. 1.3 g/cm ³
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	240 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	270 0.1 mm
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , lower limit	4000 mPas
Shear viscosity, Klüber method: PN 008@DIN 53019-1, equipment: rotational viscometer, 25°C, 300 s ⁻¹ , upper limit	8000 mPas
Kinematic viscosity of the base oil, 100°C, calculated data	approx. 20 mm ² /s
Kinematic viscosity of the base oil, 40°C, calculated data	approx. 130 mm ² /s
Copper corrosion, DIN 51811, 24 h, 100°C	1 - 100 - 24 corrosion degree
SKF-EMCOR, DIN 51802, based on standard, Klüber method: 3 % NaCl solution, 164 h	≤ 3 corrosion degree
Flow pressure, DIN 51805-2, -40°C	≤ 1400 mbar
Dropping point, DIN ISO 22286 / IP 396	≥ 240 °C
Speed factor (n x dm)	approx. 1000000 mm/min
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication München GmbH & Co. KG /
Geisenhainerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.