Product Datasheet: ARC S2(E)

100% solids, ceramic reinforced thin film coating to protect structures against erosion, abrasion, and corrosion. ARC S2(E) industrial coating is designed to:

- Protect against corrosion and erosion
- Provide improved material flow properties
- Apply by brush, roller, airless or plural component spraying

Application Areas

- Tank lining
- Structural steel
- Pipe ID & OD
- Fans & housings Condensers
- Heat exchangers
- Hoppers
- Absorber modules
- Pumps & valves

Features and Benefits

- Abrasion resistant surface Extends equipment life
- Reduces downtime
- High gloss, low drag surface
 - Improves material flow Enhances efficiency
- High adhesive strength
 - Prevents underfilm corrosion
- 100% solids; no VOCs; no free isocyanates
 - Enhances safe use
 - No shrinkage on cure
 - Resists permeation
- Low viscosity: brush, roller or spray applied coating
 - Easy to apply
 - Saves repair time

1.5 liter and 5 liter kits include tools. Color: Gray or Green

Packaging and Coverage

1.5 liter kit covers 4.00 m² (43.0 ft²)

5 liter kit covers 13.33 m² (143.5 ft²)

16 liter kit covers 42.67 m² (459.2 ft²)

Note: Components are pre-measured & pre-weighed. Each kit includes mixing and application instructions.

1125 ml cartridge covers 3.00 m² (32.29 ft²)

Nominal, based on 375 µm (15 mil)

Technical Data

Composition Matrix	A modified epoxy resin reacted with an aliphatic curing agent		
Reinforcement	Proprietary blend of fine ceramic reinforcements		
Cured Density		1.5 g/cc	94 lb/ cu.ft.
Compressive Strength	(ASTM D 695)	830 kg/cm² (81.4 MPa)	11,800 psi
Flexural Strength	(ASTM D 790)	422 kg/cm² (41.4 MPa)	6,000 psi
Tensile Adhesion	(ASTM D 4541)	436 kg/cm² (42.8 MPa)	6,200 psi
Tensile Strength	(ASTM D 638)	362 kg/cm² (35.5 MPa)	5,150 psi
Tensile Elongation	(ASTM D 638)	3.2%	
Flexural Modulus	(ASTM D 790)	4.1 x 10 ⁴ kg/cm ² (4000 MPa)	5.8 x 10⁵ psi
Shore D Durometer Hardness	(ASTM D 2240)	87	
Vertical Sag Resistance, at 21°C (70°F) and 0.75 mm (30 mils)		No sag	
Cathodic Disbondment	(ASTM G 8)	Passes	
Taber Wear CS-17/1000 cycles/1 kg load	(ASTM D 4060)	58 mg loss	
Maximum Temperature (Dependent on service)	Wet Service Dry Service	52°C 80°C	125°F 175°F
Shelf life (unopened containers)	2 years [stored between 10°C (50°F) and 32°C (90°F) in dry, covered facility]		



Chesterton International GmbH Am Lenzenfleck 23, DE-85737 Ismaning, Germany Tel +49-5223-96276-0 www.arc-epc.com eu-pds © 2019 A.W. Chesterton Company eu-pds@chesterton.com

® Reaistered trademark owned and licensed by A.W. Chesterton Company in USA and other countries, unless otherwise noted.

Technical Data reflect results of laboratory tests and are intended to indicate general characteristics only. Since many actual application circumstances are beyond Chesterton's knowledge and/or control, the product user must determine the suitability of the products it intends to use for its particular purpose and assume all risks and liabilities in connection therewith. CHESTERTON DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form No. EN-084985EU



